



A

RECEIVED
116579
NO file

United States Patent [19]

Trager et al.

⁵⁰¹
[54] INJECTIONABLE VISCOELASTIC
OPHTHALMIC GEL

[76] Inventors: Seymour F. Trager, 14 Sherwood
Dr., Plainview, N.Y. 11803; Victoria
S. Chylinski, 11 Peghouse Rise, Slad
Rd., Stroud, Glos., England

[21] Appl. No.: 625,249

[22] Filed: Jun. 27, 1984

Related U.S. Application Data

[63] Continuation-in-part of Ser. No. 434,412, Oct. 14, 1982,
abandoned.

[51] Int. Cl.³ A61K 31/78

[52] U.S. Cl. 424/81; 514/912

[58] Field of Search 424/78, 81

OK
125

INJECTIONABLE VISCOELASTIC OPHTHALMIC

SP This is a continuation-in-part of Ser. No. 434,412, filed Oct. 14, 1982, now abandoned.

30 BACKGROUND OF THE INVENTION

This invention relates to ophthalmic surgery and treatment. More particularly, this invention relates to a composition particularly suitable for use as an adjunct in ophthalmic surgery.

In surgical procedures involving ocular tissue such as, for example, anterior segment surgery, it is always necessary to protect the corneal endothelium from mechanical damage. Failure to provide adequate protection can result in irreparable damage to the tissue.

Presently, ophthalmic surgical procedures are carried out in a viscoelastic medium so as to prevent mechanical damage and denudation of the tissue surfaces. Sodium hyaluronate is currently widely used as the viscoelastic substance, presenting both positive and negative facets in ophthalmic surgical procedures. Positively, the hyaluronate has been reported as protecting the corneal endothelium; however, great care must be exercised in the use of hyaluronate, and in many instances, undesirable post-operative pressure increases have been noted, with dilation and, in some instances, adhesion development between the posterior capsule and the iris.

It is an object of the present invention to provide an improved injectionable ocular surgical and treatment adjunct.

It is a further object of the present invention to provide an improved injectionable viscoelastic solution which is nonreactive with ocular tissues.

A further object of the present invention is to provide an improved injectionable viscoelastic solution which may be employed without postoperative complications in such anterior segment surgical procedures as cataract removal, corneal transplants, penetrating keratoplasty, correctional treatment of bullous rhegmatogenous retinal detachment and the like.

These and other objects will become apparent from the disclosure which follows.

STATEMENT OF THE INVENTION

In accordance with the present invention, there is provided an improved viscoelastic gel comprising:
 an acrylamide polymer selected from polyacrylamide
 and polymethacrylamide
 sodium chloride
 potassium chloride
 calcium chloride
 magnesium chloride hexahydrate
 sodium acetate
 buffer
 water

In this particularly effective formulation, it has been found that the effectiveness thereof is achieved by compounding the constituents thereof within certain, well-defined ranges and by employing polyacrylamides and polymethacrylamides of certain, well-defined molecular weights.

The polyacrylamides found to be effective in the present compositions are polymers having a molecular weight of from about 1 to about 6 million, produced by the polymerization of acrylamide, methacrylamide, or mixtures thereof by methods known to the art. Preferably, the polymers have a molecular weight on the order of about 5 million. Inclusion of the polymer in the gel formulation is maintained within from about 2 to about

5 percent by weights, preferably from about 3.5 to about 4.5 percent by weight, and most preferably about 4.0 percent by weight.

The remaining constituents of the formulation are present in the following amounts, based upon percent by weight:

T0030X

sodium chloride	0.4-8.6
potassium chloride	0.075-0.3
calcium chloride	0.04-0.33
magnesium chloride hexahydrate	0.02-0.04
sodium acetate	0.3-0.4
buffer	0.15-0.20
water	remainder

A particularly suitable formulation is a 4.0 percent by weight polymer gel containing 0.49 percent by weight sodium chloride, 0.075 percent by weight potassium chloride, 0.048 percent by weight calcium chloride, 0.03 magnesium chloride hexahydrate and 0.17 sodium citrate dihydrate as the buffering agent.

While sodium citrate dihydrate is preferred as a gel buffer, other pharmaceutically acceptable buffering agents such as sodium phosphates and sodium borates may be advantageously employed.

The composition is formulated by autoclaving at sterilization temperatures an 8-10 percent by weight of the polymer and admixing the sterile gel with the premixed salt solution. It has been found that compounding of the polymer with the salt constituents prior to sterilization results in a rise in pH above an acceptable level.

The viscoelastic gels of the present invention are, as previously stated, particularly useful in ocular surgical procedures as a surgical adjunct, exhibiting:

- (a) protective properties for corneal endothelium, iris and retinal tissue;
- (b) superior properties as an aqueous humor replacement;
- (c) ability to maintain a deep anterior chamber during operative procedures;
- (d) ability to separate effectively tissue surfaces and thereby minimize adhesion; and
- (e) biocompatibility with intra ocular tissues.

The particular effectiveness of this specific formulation as an adjunct in ophthalmic surgery is a direct result of its balanced viscoelastic properties. The viscous nature thereof provides mechanical protection for tissues (iris, retina) and cell layers (corneal endo- and epithelium) which may be exposed to mechanical damage during surgery. Further, due to the physical properties of the formulation, the gel does not flow out of the anterior chamber, providing a deep anterior chamber during surgical manipulations.

The following example serves to illustrate the present invention.

EXAMPLE 1

An autoclaved polyacrylamide having a molecular weight of about 5 million was admixed with a premixed salt solution to yield the following homogenous gel composition:

T0031X

Component	Percent by Weight
polyacrylamide	4.0
sodium chloride	0.049
potassium chloride	0.075

-continued

Component	Percent by Weight
calcium chloride	0.048
magnesium chloride hexahydrate	0.030
sodium acetate	0.390
sodium citrate dihydrate	0.170
water	remainder

The gel, when utilized in standard testing for biocompatibility and irritation determinations, produced no adverse reactions in the ocular tissues of the test animals.

EXAMPLE 2

An autoclaved polymethacrylate having a molecular weight of about 5 million was admixed with a premixed salt solution to yield the following homogenous gel composition:

T0040X

Component	Percent by Weight
polymethacrylamide	4.0
sodium chloride	0.049
potassium chloride	0.075
calcium chloride	0.048
magnesium chloride hexahydrate	0.030
sodium acetate	0.390
sodium citrate dihydrate	0.170
water	remainder

The gel, when utilized in standard testing for biocompatibility and irritation determinations, produced no adverse reactions in the ocular tissues of the test animals.